IEC 60747-5-10

Edition 1.0 2019-12

INTERNATIONAL STANDARD

colour inside

Semiconductor devices –
Part 5-10: Optoelectronic devices – Light emitting diodes – Test method of the internal quantum efficiency based on the room-temperature reference point

SIST Preview
(https://ecommerce.sist.si)

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/1b2b34ba-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

IEC 60747-5-10:2019-12(en)

THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org
The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary
67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

SIST Preview
(https://ecommerce.sist.si)

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/1b2b34ba-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

IEC 60747-5-10

Edition 1.0 2019-12

INTERNATIONAL STANDARD

colour inside

Semiconductor devices – Part 5-10: Optoelectronic devices – Light emitting diodes – Test method of the internal quantum efficiency based on the room-temperature reference point

SIST Preview
(https://ecommerce.sist.si)

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/1b2b34ba-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 31.080.99

ISBN 978-2-8322-7655-6

Warning! Make sure that you obtained this publication from an authorized distributor.

® Registered trademark of the International Electrotechnical Commission

CONTENTS

FOREWORD 3
1 Scope 5
2 Normative references 5
3 Terms, definitions and abbreviated terms 5
3.1 Terms and definitions 5
3.2 Abbreviated terms 7
4 Measuring methods 7
4.1 Basic requirements 7
4.1.1 Measuring conditions 7
4.1.2 Measuring instruments and equipment 8
4.2 Purpose 8
4.3 Measurement 8
4.3.1 Measurement setup 8
4.3.2 Measurement principle 8
4.3.3 Measurement sequence 8
5 Test report 10
Annex A (informative) Test example 11
Bibliography 16

Figure 1 – Test flow 10
Figure A.1 – Radiant power as a function of forward current 11
Figure A.2 – Relative EQE as a function of forward current 12
Figure A.3 – Determination of peak EQE point in the relative EQE curve 12
Figure A.4 – Conversion to the normalized variables of X and Y 13
Figure A.5 – Coefficients a_1 and a_2 as a function of X 13
Figure A.6 – Verification of a reference point in the a_2 curve 14
Figure A.7 – IQE as a function of forward current 14

Table A.1 – Summary of test report 15

SIST Preview
(https://ecommerce.sist.si)

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SEMICONDUCTOR DEVICES –

Part 5-10: Optoelectronic devices – Light emitting diodes – Test method of the internal quantum efficiency based on the room-temperature reference point

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

Preview
(https://ecommerce.sist.si)
IEC 60747-5-10:2019
https://standards.iteh.ai/catalog/standards/sist/ecommerce/iec-60747-5-10-2019

International Standard IEC 60747-5-10 has been prepared by subcommittee 47E: Discrete semiconductor devices, of IEC technical committee 47: Semiconductor devices.

The text of this International Standard is based on the following documents:

CDV	Report on voting
47E/652/CDV	47E/677/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60747 series, published under the general title *Semiconductor devices*, can be found on the IEC website.

Future standards in this series will carry the new general title as cited above. Titles of existing standards in this series will be updated at the time of the next edition.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

SIST Preview
(https://ecommerce.sist.si)

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/1b2b34ba-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

SEMICONDUCTOR DEVICES –

Part 5-10: Optoelectronic devices – Light emitting diodes – Test method of the internal quantum efficiency based on the room-temperature reference point

1 Scope

This part of IEC 60747 specifies the measuring method of the internal quantum efficiency (IQE) of single light emitting diode (LED) chips or packages without phosphor. White LEDs for lighting applications are out of the scope of this document. This document utilizes only the relative external quantum efficiency (EQE) measured at an operating room temperature. In order to identify the reference IQE, an operating current corresponding to the injection efficiency of 100 % is found and the radiative efficiency is determined by the infinitesimal change of the relative EQE at that point. The IQE as a function of current is then calculated from the relative ratio of the EQEs to the value at the reference point, which is called room-temperature reference-point method (RTRM).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

SIST Preview
(https://ecommerce.sist.si)

IEC 60747-5-6:2016, *Semiconductor devices – Part 5-6: Optoelectronic devices – Light emitting diodes*

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/162b540a-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1.1
internal quantum efficiency
η_{IQE}
ratio of the number of photons emitted from the active region per unit time to the number of electrons injected into the LED per unit time

$$\eta_{\mathrm{IQE}} = \frac{\Phi_{\mathrm{e,active}} / h\bar{\nu}}{I_{\mathrm{F}} / q}$$

where

$\Phi_{\mathrm{e,active}}$ is the radiant power emitted from the active region

$h\bar{\nu}$ is the mean photon energy

I_{F} is the forward current

q is the elementary charge

Note 1 to entry: It is in general a function of ambient temperature (T_a) and forward current (I_F).

[SOURCE: IEC 60747-5-8:2019, 3.2.4, modified – The note has been added.]

3.1.2
external quantum efficiency
η_{EQE}
ratio of the number of photons emitted into the free space per unit time to the number of electrons injected into the LED per unit time

$$\eta_{EQE} = \frac{\Phi_e / h\bar{\nu}}{I_F / q}$$

where

Φ_e is the radiant power

Note 1 to entry: It is in general a function of ambient temperature (T_a) and forward current (I_F).

[SOURCE: IEC 60747-5-8:2019, 3.2.3, modified – The note has been added.]

3.1.3
light extraction efficiency
η_{LEE}
ratio of the number of photons emitted into the free space to the number of photons emitted from the active region

SIST Preview
(https://ecommerce.sist.si)

$$\eta_{LEE} = \frac{\Phi_e}{\Phi_{e,active}}$$

Note 1 to entry: It is in general independent of forward current (I_F) at certain ambient temperature (T_a).

IEC 60747-5-10:2019

[SOURCE: IEC 60747-5-8:2019, 3.2.5, modified – The note has been added.]

3.1.4
injection efficiency
η_{IE}
ratio of the number of electrons injected into the active region per unit time to the number of electrons injected into the LED per unit time

$$\eta_{IE} = \frac{I_{F,active}}{I_F}$$

where

$I_{F,active}$ is the portion of the forward current injected into the active region

[SOURCE: IEC 60747-5-8:2019, 3.2.6]

3.1.5
radiative efficiency
η_{RE}
ratio of the number of photons emitted from the active region per unit time to the number of electrons injected into the active region per unit time

$$\eta_{RE} = \frac{\Phi_{e,active} / h\bar{\nu}}{I_{F,active} / q}$$

[SOURCE: IEC 60747-5-8:2019, 3.2.7, modified – The note has been removed.]

3.1.6
peak EQE point
set of operating conditions of the forward current and radiant power at which the external quantum efficiency (EQE) is the maximum for a given temperature

Note 1 to entry: The forward current and radiant power at the peak EQE point are denoted as I_{peak} and Φ_{peak}, respectively.

3.1.7
normalized variables of X and Y
converted quantities of current and radiant power, defined as:

$$X = \sqrt{\Phi_e(I_F) / \Phi_e(I_{peak})}$$

$$Y = I_F / I_{peak}$$ f

3.1.8
coefficients of a_1 and a_2
coefficients of the quadratic equation of Y in X, i.e., $Y = a_1 X + a_2 X^2$

Note 1 to entry: a_1 and a_2 change slowly enough according to the forward current as compared to X and Y, but should be treated as a function of the forward current in the data analysis.

3.1.9
reference point
operating point at which a_2 is the minimum

SIST Preview
(https://standards.iteh.ai)

Note 1 to entry: a_2, X, and Y at the reference point are represented by $a_{2,ref}$, X_{ref}, and Y_{ref}, respectively. The forward current at the reference point is denoted as $I_{F,ref}$.

3.2 Abbreviated terms

IEC 60747-5-10:2019
https://standards.iteh.ai/catalog/standards/sist/1b2b34ba-4866-45c0-95be-0107be9a02ff/iec-60747-5-10-2019

EQE external quantum efficiency

IQE internal quantum efficiency

LED light emitting diode

RTRM room-temperature reference-point method

4 Measuring methods

4.1 Basic requirements

4.1.1 Measuring conditions

a) Temperature

If not specified, measurements shall be made at an ambient temperature (T_a) of (25 ± 3) °C in a condition of free air.

b) Humidity

When the humidity condition is not specified, relative humidity shall be between 45 % RH and 85 % RH.

c) Precaution

In some cases, measurements change because of heat generation in the test LED over time. In that case, it is necessary to decide on the measurement time; otherwise, the measurement shall be performed after reaching thermal equilibrium. Thermal equilibrium can be considered to have been achieved if doubling the time between the application of power and the measurement causes no change in the indicated result within the precision of the measurement instruments.

4.1.2 Measuring instruments and equipment

The measuring instruments and equipment shall be the same as listed in IEC 60747-5-6:2016, 6.1.2.

4.2 Purpose

To measure the internal quantum efficiency (IQE) at an operating temperature of the LED without any parameter assumptions under established conditions. The method utilizes just the experimental curve of radiant power (Φ_e) as a function of forward current (I_F) measured at an ambient temperature (T_a).

4.3 Measurement

4.3.1 Measurement setup

All of the tests should be performed under well-certified and defined conditions to avoid any external disturbances. Basic measurement setup schematics are the same as listed in IEC 60747-5-6.

The measurement of the forward voltage at a specified forward current is listed in IEC 60747-5-6:2016, 6.2.

The measurement of the radiant power at a specified current is listed in IEC 60747-5-6:2016, 6.11.

The measurement of the emission spectrum distributions, peak wavelength (λ_p), and spectral half bandwidth of the LED are listed in IEC 60747-5-6:2016, 6.15.

SIST Preview
(https://ecommerce.sist.si)

The measurement of the pulse current is listed in IEC 60747-5-6:2016, 6.8.

4.3.2 Measurement principle

IEC 60747-5-10:2019

First, the measurement procedure seeks to find the IQE at the reference point η_{IQE} where the injection efficiency (η_{IE}) is supposed to be 100 % and the radiative efficiency (η_{RE}) is calculated from the infinitesimal change of the relative external quantum efficiency (η_{EQE}). Once the IQE at the reference point is exactly found, the IQE at any other point is calculated by the relative ratio of EQE values to the one at the reference point, i.e., $\eta_{IQE}(I_F) = [\eta_{EQE}(I_F)/\eta_{EQE}(I_{F,ref})] \cdot \eta_{IQE}(I_{F,ref})$.

The injection efficiency becomes the maximum when a_2 becomes the minimum. However, the uncertainty of the injection efficiency being exactly 100 % and its criterion should be established in the future.

4.3.3 Measurement sequence

The IQE measurement should proceed according to the following ten sequential steps as shown in Figure 1. A test example is given in Annex A.

- Step 0: Test environmental specifications

  All of the tests should be performed under well-certified and defined conditions to avoid any external disturbances. An example of the test's environmental specifications is listed in Annex A. The specifications should include such parameters as the humidity, the current driving condition, and the detector for radiant power measurement.

- Step 1: Acquire N data consisting of radiant power and current

  Radiant power is measured as a function of current from 0 to I_{max}, and a set of N data consisting of the radiant power (Φ_e) and forward current is obtained. The radiant power does not have to be the absolute value. It is recommended to divide by at least 100 in the current range from 0 to I_{peak}. It is also recommended to divide the current range from I_{peak} to I_{max} by 100 or more.

- Step 2: Draw a relative external quantum efficiency (EQE) curve

  The relative EQE is obtained by dividing the radiant power by the forward current, i.e. $\eta_{\mathrm{IQE}}(I_{\mathrm{F}}) = \Phi_{\mathrm{e}}(I_{\mathrm{F}})/ I_{\mathrm{F}}$.

- Step 3: Find the peak point in the relative EQE curve

  Find a set of operating conditions of the forward current (I_{peak}) and radiant power (Φ_{peak}) at which the relative EQE is the maximum.

- Step 4: Convert the radiant power and current to the normalized variables of X and Y

  Find the normalized variables of X and Y from the following definitions of $X(I_{\mathrm{F}}) = \sqrt{\Phi_{\mathrm{e}}(I_{\mathrm{F}}) / \Phi_{\mathrm{e}}(I_{\mathrm{peak}})}$ and $Y(I_{\mathrm{F}}) = I_{\mathrm{F}}/I_{\mathrm{peak}}$.

- Step 5: Find the coefficients of a_1 and a_2

  Find a set of $\{a_{1,i}\}$ and $\{a_{2,i}\}$ by solving the following two simultaneous equations with the two nearest experimental data (X_i, Y_i) and (X_{i+1}, Y_{i+1}).

$$\begin{aligned} Y_i &= a_{1,i} X_i + a_{2,i} X_i^2 \\ Y_{i+1} &= a_{1,i} X_{i+1} + a_{2,i} X_{i+1}^2 \end{aligned} .$$

- Step 6: Find a reference point in a_2 versus X curve

  When a_2 is represented by a function of X, an operating point at which a_2 is the minimum is selected as a reference point. I_{F}, a_1, a_2, X, and Y at the reference point are represented by $I_{\mathrm{F,ref}}$, $a_{1,\mathrm{ref}}$, $a_{2,\mathrm{ref}}$, X_{ref}, and Y_{ref}, respectively.

- Step 7: Calculate the internal quantum efficiency (IQE) at a reference point

  Using $a_{1,\mathrm{ref}}$, $a_{2,\mathrm{ref}}$ and X_{ref} at the reference point, calculate the IQE from the following formula:

SIST Preview
(https://ecommerce.sist.si)

$$\eta_{\mathrm{IQE,ref}} = \frac{a_{2,\mathrm{ref}} X_{\mathrm{ref}}^2}{a_{1,\mathrm{ref}} X_{\mathrm{ref}} + a_{2,\mathrm{ref}} X_{\mathrm{ref}}^2} .$$

IEC 60747-5-10:2019
https://ecommerce.sist.si/catalog/standards/sist/1b2b5[illegible]95be-0107be9a02ff/iec-60747-5-10-2019

- Step 8: Find the IQE at an arbitrary current (I_{F})

  Determine the IQE at any current using the EQE curve at an arbitrary current and the internal quantum efficiency at the reference point as follows:

$$\eta_{\mathrm{IQE}}(I_{\mathrm{F}}) = \eta_{\mathrm{IQE}}(I_{\mathrm{ref}}) \frac{\eta_{\mathrm{EQE}}(I_{\mathrm{F}})}{\eta_{\mathrm{EQE}}(I_{\mathrm{ref}})} .$$

- Step 9: Create the test report

  Fill in the test report given in Annex A.