



SLOVENSKI STANDARD

SIST EN ISO 1167-2:2006

01-april-2006

Nadomegl' a:
SIST EN 921:1997

**Plastomerne cevi, fittingi in spoji za pretok tekoč in in plinov ņ Ugotavljanje
odpornosti proti notranjemu tlaku ņ 2. del: Priprava cevi za preskus (ISO 1167-
2:2006)**

Thermoplastics pipes, fittings and assemblies for the conveyance of fluids -
Determination of the resistance to internal pressure - Part 2: Preparation of pipe test
pieces (ISO 1167-2:2006)

Rohre, Formstücke und Bauteilkombinationen aus thermoplastischen Kunststoffen für
den Transport von Flüssigkeiten - Bestimmung der Widerstandsfähigkeit gegen inneren
Überdruck - Teil 2: Vorbereitung der Rohr-Probekörper (ISO 1167-2:2006)

Tubes, raccords et assemblages en matieres thermoplastiques pour le transport des
fluides - Détermination de la résistance a la pression interne - Partie 2: Préparation des
épreuves tubulaires (ISO 1167-2:2006)

Ta slovenski standard je istoveten z: EN ISO 1167-2:2006

ICS:

23.040.20	Cevi iz polimernih materialov	Plastics pipes
23.040.45	Fittingi iz polimernih materialov	Plastics fittings

SIST EN ISO 1167-2:2006

en

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

FINAL DRAFT
prEN ISO 1167-2

October 2005

ICS 23.040.45; 23.040.20

Will supersede EN 921:1994

English Version

**Thermoplastics pipes, fittings and assemblies for the
conveyance of fluids - Determination of the resistance to internal
pressure - Part 2: Preparation of pipe test pieces (ISO/FDIS
1167-2:2005)**

Tubes, raccords et assemblages en matières
thermoplastiques pour le transport des fluides -
Détermination de la résistance à la pression interne - Partie
2: Préparation des éprouvettes tubulaires (ISO/FDIS 1167-
2:2005)

Rohre, Formstücke und Zubehör aus thermoplastischen
Kunststoffen für den Transport von Flüssigkeiten -
Bestimmung der Widerstandsfähigkeit gegen inneren
Überdruck - Teil 2: Herstellung der Rohr-Probekörper
(ISO/FDIS 1167-2:2005)

This draft European Standard is submitted to CEN members for parallel formal vote. It has been drawn up by the Technical Committee CEN/TC 155.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

prEN ISO 1167-2:2005 (E)

Foreword

This document (prEN ISO 1167-2:2005) has been prepared by Technical Committee ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids" in collaboration with Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This document is currently submitted to the parallel Formal Vote.

This document will supersede EN 921:1994.

Endorsement notice

The text of ISO 1167-2:2005 has been approved by CEN as prEN ISO 1167-2:2005 without any modifications.

SIST Preview
(<https://ecommerce.sist.si>)

[SIST EN ISO 1167-2:2006](#)

<https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006>

INTERNATIONAL
STANDARDISO
1167-2First edition
2006-02-01

**Thermoplastics pipes, fittings and
assemblies for the conveyance of
fluids — Determination of the resistance
to internal pressure —****Part 2:
Preparation of pipe test pieces**

*Tubes, raccords et assemblages en matières thermoplastiques pour le
transport des fluides — Détermination de la résistance à la pression
interne —*

Partie 2: Préparation des éprouvettes tubulaires

SIST EN ISO 1167-2:2006

<https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006>

Reference number
ISO 1167-2:2006(E)

© ISO 2006

ISO 1167-2:2006(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

SIST Preview
(<https://ecommerce.sist.si>)

SIST EN ISO 1167-2:2006

<https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	2
5 Test pieces	2
5.1 Extruded test pieces	2
5.2 Injection-moulded tubular test pieces	2
5.3 Measurement of dimensions	2
6 Test report	2
Bibliography	4

SIST Preview
(<https://ecommerce.sist.si>)

[SIST EN ISO 1167-2:2006](https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006)

<https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006>

ISO 1167-2:2006(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1167-2 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This first edition of ISO 1167-2, together with ISO 1167-1, cancels and replaces ISO 1167:1996 and, together with ISO 1167-3, cancels and replaces ISO 12092:2000, of which it constitutes a technical revision.

ISO 1167 consists of the following parts, under the general title *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure*:

- *Part 1: General method*
- *Part 2: Preparation of pipe test pieces*
- *Part 3: Preparation of components*
- *Part 4: Preparation of assemblies*

Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure —

Part 2: Preparation of pipe test pieces

1 Scope

This part of ISO 1167 specifies the dimensions and method for preparation of extruded, or injection-moulded tubular, test pieces used to determine the resistance of thermoplastics pipes to internal hydrostatic pressure according to ISO 1167-1.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions*

3 Principle

Pipe test pieces may be obtained by extrusion or injection-moulding. The extruded test pieces are used for material and pipe testing, whereas the injection-moulded tubular test pieces are used for testing injection moulding materials only.

The injection-moulded tubular test pieces make it possible to determine the time-related behaviour of the injection moulding material for fittings under hydrostatic pressure and under the same conditions as specified for extruded pipes. It is possible to extrapolate the results in accordance with a method such as that specified in ISO 9080 in order to determine the MRS (minimum required strength) and to classify the material using ISO 12162. The tubular test pieces also make it possible to verify individual points on previously established stress/time regression curves as a minimum material test requirement.

NOTE If the compound used for the injection-moulding of components can also be extruded, then its time-related behaviour can be investigated using either injection-moulded or extruded tubular test pieces.

After conditioning, test pieces consisting of a portion of pipe sufficient to provide the required free length as a function of the diameter of the pipe are subjected to a specified internal hydrostatic pressure or stress for a specified period of time or until the test piece(s) fail(s), in accordance with ISO 1167-1.

The number of test pieces, conditioning and details of the test report are given in ISO 1167-1.

ISO 1167-2:2006(E)

4 Apparatus

- 4.1 End caps**, as specified in the standard making reference to ISO 1167-1.
- 4.2 Means of measuring the wall thickness**, conforming to ISO 3126.
- 4.3 Means of measuring the mean outside diameter of the pipe**, conforming to ISO 3126, e.g. Pi-tape.

5 Test pieces

5.1 Extruded test pieces

5.1.1 Free length

The free length, l_0 , of the pipe between the end caps shall be at least three times the nominal outside diameter d_n , with a minimum of 250 mm.

If, for pipes with d_n greater than 315 mm, the specified minimum free length cannot be achieved, a shorter free length may be chosen with a minimum of two times d_n , unless otherwise specified in the referring standard or specification.

5.1.2 Total length

For type B end caps (see ISO 1167-1:2006, 5.1), the total length of the test piece shall be such that movement of the test piece between the end caps is accommodated during the test, thus making allowance for thermal expansion.

5.2 Injection-moulded tubular test pieces

Injection-moulded test pieces shall conform to the following requirements for the dimensions shown in Figure 1. <https://ecommerce.sist.si/catalog/standards/sist/8c0c512b-04d4-4208-95e7-63fc5c24f247/sist-en-iso-1167-2-2006>

The nominal outside diameter d_n of the test pieces shall be between 25 mm and 110 mm inclusive. The wall thickness will depend on the material concerned.

The free length l_0 of the test pieces, excluding the ends, shall be $3d_n$, except for test pieces $d_n \geq 50$ mm, for which the minimum free length shall be 140 mm.

Injection-moulded test pieces with a longitudinal fusion line and both ends open should preferably be used for comparative and investigative purposes only.

The injection-moulding parameters can strongly influence the stresses in the injection-moulded test piece.

5.3 Measurement of dimensions

If necessary for the calculation of the test pressure (see ISO 1167-1:2006, 7.2), find and determine, in accordance with ISO 3126, the minimum wall thickness and the mean outside diameter of the free length of the test piece, using apparatus conforming to 4.2 and 4.3. These measurements shall be used for further calculations. The rounding up procedure of ISO 3126 shall not be applied.

6 Test report

Record the information required in order to comply with ISO 1167-1:2006, Clause 11 and include the method of manufacture of the test piece, i.e. by extrusion or by injection moulding.