

ISO 15874-2:2013/~~FDAM~~AMD 1:2018(E)

ISO/TC 138/SC 2 N

Date: 2018-~~03-14~~07-01

ISO 15874-2:2013/~~FDAM~~AMD 1

ISO/TC 138/SC 2/WG 1

Secretariat: SNV

Plastic piping systems for hot and cold water installations — Polypropylene (PP) —
Part 2: Pipes — Amendment 1

Systèmes de canalisations en plastique pour les installations d'eau chaude et froide -
- Polypropylène (PP) -- Partie 2: Tubes -- Amendement 1

SIST Preview
(<https://ecommerce.sist.si>)

ISO 15874-2:2013/Amd 1:2018

<https://ecommerce.sist.si/catalog/standards/sist/98cc8bc9-c27e-4e4c-9c7d-cb66d28fb37a/iso-15874-2-2013-amd-1-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 155, *Plastics piping systems and ducting systems*, in collaboration with ISO Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastic piping systems for hot and cold water installations — Polypropylene (PP) — Part 2: Pipes

Page 10, Table 5

Replace Table 5 with the new Table 5 below, where larger dimensions (180 mm to 250 mm) have been added. The dimensions of 12 mm to 160 mm have been unchanged from the ISO 15874-2:2013 version.

Table 5 — Pipe dimensions for dimension class A

Dimensions in millimetres

Nominal size DN/OD	Nominal outside diameter	Mean outside diameter ^b		Pipe series						
				S 8 ^a	S 6,3 ^a	S 5	S 4 ^a	S 3,2	S 2,5	S 2
				Wall thicknesses						
	d_n	$d_{em,min}$	$d_{em,max}$	e_{min} and e_n						
12	12	12	12,3	1,8	1,8	1,8	1,8	1,8	2,0	2,4
16	16	16	16,3	1,8	1,8	1,8	1,8	2,2	2,7	3,3
20	20	20	20,3	1,8	1,8	1,9	2,3	2,8	3,4	4,1
25	25	25	25,3	1,8	1,9	2,3	2,8	3,5	4,2	5,1
32	32	32	32,3	1,9	2,4	2,9	3,6	4,4	5,4	6,5
40	40	40	40,4	2,4	3,0	3,7	4,5	5,5	6,7	8,1
50	50	50	50,5	3,0	3,7	4,6	5,6	6,9	8,3	10,1
63	63	63	63,6	3,8	4,7	5,8	7,1	8,6	10,5	12,7
75	75	75	75,7	4,5	5,6	6,8	8,4	10,3	12,5	15,1
90	90	90	90,9	5,4	6,7	8,2	10,1	12,3	15,0	18,1
110	110	110	111	6,6	8,1	10,0	12,3	15,1	18,3	22,1
125	125	125	126,2	7,4	9,2	11,4	14,0	17,1	20,8	25,1
140	140	140	141,3	8,3	10,3	12,7	15,7	19,2	23,3	28,1
160	160	160	161,5	9,5	11,8	14,6	17,9	21,9	26,6	32,1
180	180	180	181,7	10,7	13,3	16,4	20,1	24,6	29,9	36,1
200	200	200	201,8	11,9	14,7	18,2	22,4	27,4	33,2	40,1
225	225	225	227,1	13,4	16,6	20,5	25,2	30,8	37,4	45,1
250	250	250	252,3	14,8	18,4	22,7	27,9	34,2	41,5	50,1
^a Only valid for PP-RCT.										
^b The level of the tolerances conforms to Grade A in ISO 11922-1[2].										